

Investigating the Causes of Failure in Posterior Amalgam and Composite Restorations: A Cross-Sectional Study

Fahimeh Feili ^{1,2} , Athar Nazifi ³ , Hossein Seidkhani ⁴ , Elham Shafiei ⁵ 

¹ Department of Restorative Dentistry, School of Dentistry, Ilam University of Medical sciences, Ilam, Iran

² Oral and Dental Health Research Center, Faculty of Dentistry, Ilam University of Medical sciences, Ilam, Iran

³ School of Dentistry, Ilam University of Medical sciences, Ilam, Iran

⁴ Department of Biostatistics, School of Health, Ilam University of Medical sciences, Ilam, Iran

⁵ Psychosocial Injuries Research Center, Ilam University of medical Sciences, Ilam, Iran.

Article Info

Article type:

Research Article

Article History:

Received: May. 20, 2024

Revised: Jun. 01, 2024

Accepted: Jun. 08, 2024

Published Online: Sep. 10, 2024

✉ Correspondence to:

Elham Shafiei

School of Dentistry, Ilam
University of Medical sciences,
Ilam, Iran

Email:

shafiei-e@medilam.ac.ir

ABSTRACT

Introduction: Understanding the reasons for retreatment of dental restorations is crucial to preventing potential tooth failure. Due to limited information on retreatment causes in our region, this study aims to compare the factors leading to the failure of posterior amalgam and composite restorations.

Materials & Methods: This cross-sectional, observational study was conducted on patients referred to the restorative department of Ilam Faculty of Dentistry and private clinics who required retreatment of existing posterior restorations. Failure criteria for posterior restorations were evaluated based on established reference guidelines.

Results: The study found that secondary caries had an odds ratio (OR) of 3.08 (95% CI: 2.85 – 3.29; $p < 0.001$), indicating a strong association with restoration failure. Additionally, restoration fractures were significantly correlated with retreatment, with an adjusted OR of 2.50 (95% CI: 2.46 – 2.86; $p < 0.001$).

Conclusion: Secondary caries emerged as the most common reason for retreatment, regardless of whether composite or amalgam materials were used. Restoration fractures also significantly contributed to the need for retreatment. Therefore, it is essential to consider factors such as restoration material, classification, and the number of restoration levels to reduce the likelihood of retreatment.

Keywords: Dental Restoration Failure, Dental Amalgam, Composite Resins, Retreatment

➤ How to cite this paper

Feili F, Nazifi A, Seidkhani H, Shafiei E. Investigating the Causes of Failure in Posterior Amalgam and Composite Restorations: A Cross-Sectional Study. J Bas Res Med Sci. 2024; 11(4):28-33.

Introduction

Dentists spend a significant amount of time each year replacing failed restorations. It is estimated that 50% of a dentist's time is devoted to replacing defective restorations. Studies have shown that, on average, about one-third of all existing restorations at any given time may be considered failed for various reasons (1, 2).

When a restoration is replaced, the size of the cavity is typically enlarged by 0.2-0.5 mm, weakening the remaining tooth structure. As restorations are replaced, the cavities become larger, making both the tooth and the restorations more fragile (3). While some teeth can withstand multiple restorative replacements without requiring endodontic or crown treatments, placing effective, long-term restorations is crucial to reducing the overall cost of dental care (4).

Research indicates that secondary decay around amalgam restorations is the most common reason for retreatment, with many studies identifying it as the primary factor (1). However, studies by Okasa (5) and Gharechahi (6) in 2024 suggest that tooth fracture may be an even more frequent cause of replacement.

Dental composites also have limitations. Proper isolation is crucial due to their high technical sensitivity (7). Additionally, they exhibit greater wear, especially in high-stress areas and over time in regions lacking marginal enamel for bonding (7, 8). The distinction between composite and amalgam in restoration failure is not well understood (9, 10).

Understanding the reasons for dental restoration retreatment can help prevent future tooth failures. Given changes in people's attitudes, dental knowledge, and the desire for different types of posterior restorations, this study aims to identify the causes of failure in posterior amalgam restorations in both vital and non-vital teeth, as well as in composite restorations.

Materials and methods

This cross-sectional study utilized electronic dental record (EDR) data from patients referred to the restorative department of the Dental School and various private clinics. Patients were monitored for the need for retreatment of existing restorations in posterior teeth.

Factors such as age, gender, tooth location, jaw position, type of restoration, reasons for inadequate treatment, and factors related to the causes of posterior restoration failure—including amalgam blue, marginal ditching, secondary decay, proximal overhang, incorrect proximal contact, loss of contour, cusp fracture, wear, staining, and restoration fracture—were examined for their potential impact on treatment success.

The causes of failure of posterior amalgam restorations were investigated due to the large number of samples in both vital and non-vital teeth. Additionally, the causes of failure in posterior composite restorations were analyzed, regardless of whether the tooth was vital or not.

Patients with systemic, bone, or periodontal diseases were excluded from the study. Upon collecting the data, the final conclusion highlighted that the failure rate in non-vital posterior amalgam restorations was attributed to specific variables. Identifying the variable most strongly associated with the highest failure rate was crucial, as this information could be used for retraining and informing other dentists.

Univariate data analysis was conducted to identify the best distribution with the lowest AIC, considering a P value of less than 0.2 as statistically significant. All significant variables from the univariate analysis were included in a multivariate model. The software utilized for data analysis was STATA version 12 (STATA Corporation, College Station, TX).

Results

In the composite group, the average age was 39.5 ± 8.29 years, while in the amalgam-vital group, it was 36.72 ± 8.73 years.

Regarding the failure of posterior amalgam restorations in vital teeth, 44% of failures were attributed to secondary decay, 2% to proximal overhang, 14% to marginal ditching, 18% to amalgam blue, 10% to cusp fracture, 14% to restoration fracture, 6% to loss of contour, 12% to incorrect proximal contact, and 6% to wear.

In amalgam restorations for non-vital teeth, the results indicate that 30% of failures were due to secondary decay, 2% to proximal overhang, 6% to marginal ditching, 26% to amalgam blue, 20% to cusp fracture, 56% to restoration fracture, 12% to loss

of contour, 6% to incorrect proximal contact, and 12% to occlusal surface wear.

In posterior composite repairs, the majority (64%) of failures were attributed to secondary caries. Unlike in the case of amalgam restorations, proximal overhang and marginal ditching did not significantly contribute to the failure of posterior composite repairs.

Other causes of failure in composite restorations included 10% due to staining, 16% to cusp fracture, 34% to restoration fracture, 12% to loss of contour, 12% to incorrect proximal contact, and 8% to excessive wear of the occlusal surface.

Table 1. Frequency of Factors Contributing to Restoration Failure.

Variables	Composite	Amalgam -vital	Amalgam -non vital	P-value
Age, (years) (mean ± SE)	39.5 (8.29)	36.72 (8.73)	1.03 (1.02 – 1.05)	0.35
Sex (%)				
Female	13 (26)	20(40)	17 (34)	
Male	37 (74)	30 (60)	33 (66)	0.33
Secondary caries (%)				
Yes	32(64)	22(44)	15 (30)	
No	18 (36)	28(56)	35 (70)	0.001*
Proximal overhang (%)				
Yes	0 (0)	1 (2)	1 (2)	-
No	50 (0.2)	49 (98)	49 (98)	0.60
Amalgam Blue (%)				
No	50 (100)	41 (82)	37 (74)	-
Yes	0 (0)	9 (18)	13 (26)	<0.001*
Restoration Fracture (%)				
No	33 (66)	43(86)	22 (44)	-
Yes	17 (34)	7 (14)	28 (56)	<0.001*
Loss of Contour (%)				
No	44(88)	47 (94)	44 (88)	-
Yes	6 (12)	3 (6)	6 (12)	0.51
Proximal Improper contact (%)				
No	44 (88)	44 (88)	47 (94)	-
Yes	6 (12)	6 (12)	3 (6)	0.51
Wear (%)				

Yes	4(8)	0(0)	6(12)	-
No	46 (92)	50 (100)	44 (88)	0.05*
Cuap Fracture (%)				
No	42 (84)	45 (90)	40 (80)	-
Yes	8 (16)	5 (10)	10 (20)	0.37
Staining				
No	45 (90)	50 (100)	50 (100)	-
Yes	5 (10)	0 (0)	0 (0)	<0.001*

*Significant

Table 2. Univariate Regression Analysis of Factors Related to Restoration Failure.

Variables	Time Ratio (95% CI)	P-value
Age, (years)	1.01 (0.97 – 1.08)	0.65
Secondary caries	3.01 (2.85 – 3.19)	<0.001*
Proximal overhang	1.70 (0.86 – 2.89)	0.59
Restoration Fracture	2.49 (2.46 – 2.76)	<0.001*
Loss of Contour	1.16 (1.14 – 2.05)	0.001*
Proximal contact Incorrect	1.37 (1.27 – 1.65)	0.05*
Dental Wear	1.35 (1.20 – 2.75)	0.07
Cusp Fracture	1.54 (1.25 – 2.78)	0.001*
Staining	2.06 (1.98 – 1.19)	<0.001*

*Significant

Univariate analysis using the logarithmic distribution confirmed a significant association between secondary caries and failure (TR: 3.01; 95% CI: 2.85

– 3.19; $p < 0.001$), indicating an increased risk of failure with the presence of secondary caries (Table 2).

Table 3. Multivariate Analysis of Factors Related to Restoration Failure.

Variables	Time Ratio (95% CI)	P-value
Secondary caries	3.08 (2.85 – 3.29)	<0.001*
Restoration Fracture	2.50 (2.46 – 2.86)	<0.001*
Loss of Contour	1.31 (1.14 – 2.25)	0.001*
Cuap Fracture	1.59 (1.15 – 2.78)	0.001*
Staining	2.06 (1.98 – 1.19)	<0.001*

*Significant

After adjusting for other variables in the multivariate model, the adjusted TR for secondary caries was 3.08 (95% CI: 2.85 – 3.29; $p < 0.001$; Table 3).

Discussion

This study revealed that the primary cause of failure in composite and amalgam-vital restorations was

secondary caries, consistent with numerous previous studies (11-13) that have identified secondary caries as a significant factor in restoration failure. However, these results contradict the findings of Bokhari and Frost, who proposed tooth fracture as the most common cause of amalgam failure (14, 15).

In the current study, marginal ditching was identified as the third most common reason for retreatment of restorations. However, previous research has indicated that it ranks higher, as the second leading cause of retreatment (16, 17). Additionally, our study found that proximal overhang is among the least common causes of failure, whereas one foreign study cited it as the third most common cause of amalgam restoration failure (18). These findings underscore the importance of proper cavity preparation, correct application of the matrix and wedge, and precise reconstruction of physiological and anatomical contours.

In this study, incorrect proximal contact was identified as the fourth most common cause of vital amalgam failure. In contrast, the studies by Kimyai et al. (19) and Arandi et al. (10) reported it as the second most common reason for amalgam restoration failure. This discrepancy highlights the variability in findings across different studies and emphasizes the need for further research to understand these variations.

Furthermore, understanding the reasons for placing and replacing restorations is essential, alongside factors such as treatment planning, cavity preparation, the choice and characteristics of restorative materials, proper isolation of the area, and maintenance of oral hygiene—all of which contribute to the success of the restoration (20). Over time, this knowledge can lead to economic benefits and help prevent future failures.

Changes in dental restorative treatment patterns, driven by factors such as shifts in disease prevalence (21), the introduction of new restorative materials and techniques, and evolving attitudes of dental patients toward restorative treatments, may influence the reasons for retreatment. These changes could potentially lead to findings that differ from those of previous studies.

Limitation

This scientific study is subject to limitations stemming from the small sample size, incomplete

recording of re-treatment instances, and the omission of some important variables.

Conclusion

The most common reason for retreatment of restored teeth in composite and vital amalgam cases was secondary caries, while restoration fracture was identified as the predominant cause of replacement in non-vital amalgam cases. Given these prevalent causes of restoration failures based on the type of restoration material, it is crucial to properly classify and assess restoration levels during placement and to improve diagnostic accuracy during patient visits. Future research should consider factors such as patients' oral and dental hygiene, caries susceptibility, dietary habits, and the age of restorations, while also ensuring a sufficiently large sample size to enhance reliability.

Acknowledgements

We would like to thank our colleagues at the School of Dentistry, Ilam University of Medical Sciences, and the Clinical Research Department of the Clinical Research Development Unit, Ayatollah Taleghani Hospital, Ilam, Iran. We extend special gratitude to the patients who participated in this study.

Financial support

This study was supported by the Deputy of Research at Ilam University of Medical Sciences.

Conflict of interest

The authors declare no conflict of interest.

Authors' contributions

FF developed and designed the evaluation, collected the clinical data (NA), and drafted the manuscript. FF and ESh participated in the study's conception and design, supervised the study, and critically revised the manuscript for important intellectual content. All authors read and approved the final manuscript.

References

1. Alhoshani RN, Khan AM. Assessment of Prevalence and Causative Factors for Replacement of Composite and Amalgam Restorations: An Observational Study. *J Pharm Bioallied Sci.* 2024;16(Suppl 1):S693-S7. DOI: 10.4103/jpbs.jpbs_946_23
2. de Azevedo Miranda D, Silveira LE, Schirm JA, de Abreu Lima IL, Manzi FR. The "Phase Down" of Dental Amalgam Restorations—What are the Criteria for Replacement and Indication? *Pesqui Bras Odontoped Clin Integr.* 2024;24:e220172-e. doi.org/10.1590/pboci.2024.028
3. Wigsten E, Fransson H, Isberg PE, EndoReCo, Dawson VS. General dental practitioners' fees for root canal treatment, coronal restoration and follow-on treatment in the adult population in Sweden: A 10-year follow-up of data from the Swedish Dental Register. *J Clin Exp Dent.* 2024;10(1):e826. doi.org/10.1002/cre2.826
4. Thyvalikakath T, Siddiqui ZA, Eckert G, LaPradd M, Duncan WD, Gordan VV, et al. Survival analysis of posterior composite restorations in National Dental PBRN general dentistry practices. *J Dent.* 2024;141:104831. doi.org/10.1016/j.jdent.2024.104831
5. Oksa M, Haapanen A, Kannari L, Furuholm J, Snäll J. Surgical treatment of clinically infected mandibular fractures. *Oral Maxillofac Surg.* 2024;1-9. doi.org/10.1007/s10006-024-01213-6.
6. Gharechahi M, Rouhani A, Ahmadi AK, Davaji M. The necessity and reasons for referrals to endodontists among general dentists in Mashhad: A cross-sectional study. *Saudi Endod J.* 2024;14(1). DOI: 10.4103/sej.sej_103_23
7. Alqtaibi AY, Alghauli MA, Almuzaini SA, Alharbi AF, Alsani AA, Mubarak AM, et al. Failure and complication rates of different materials, designs, and bonding techniques of ceramic cantilever resin-bonded fixed dental prostheses for restoring missing anterior teeth: A systematic review and meta-analysis. *J Esthet Restor Dent.* 2024. doi.org/10.1111/jerd.13238
8. Sekundo C, Jung M, Muscholl C, Frese C. Oral health-related quality of life and survival analysis after preventive and restorative treatment of molar-incisor hypomineralisation. *Sci Rep.* 2024;14(1):777. doi.org/10.1038/s41598-024-51223-3
9. Poletto-Neto V, Chisini LA, Fokkinga W, Kreulen C, Loomans B, Cenci MS, et al. Single crown vs. composite for glass fiber post-retained restorations: An 8-year randomized clinical trial. *J Dent.* 2024;142:104837. doi.org/10.1016/j.jdent.2024.104837
10. Arandi NZ. Current trends in placing posterior composite restorations: Perspectives from Palestinian general dentists: A questionair study. *J Int Soc Prev Community Dent.* 2024;14(2):112-20. DOI: 10.4103/jispdc.jispdc_157_23
11. Jang Y-E, Kim Y, Kim S-Y, Kim BS. Predicting early endodontic treatment failure following primary root canal treatment. *BMC Oral Health.* 2024;24(1):327. doi.org/10.1186/s12903-024-03974-8
12. Mosavat F, Ahmadi E, Aghajani F, Ramezani S. Effect of composite radiopacity and margin location of the restoration on the diagnosis of secondary caries. *Braz Dent J.* 2024;35:e24-5583
13. Innes N, Fairhurst C, Whiteside K, Ainsworth H, Sykes D, El Yousfi S, et al. Behaviour change intervention for toothbrushing (lesson and text messages) to prevent dental caries in secondary school pupils: The BRIGHT randomized control trial. *Comm Dent Oral Epidemiol.* 2024. doi.org/10.1111/cdoe.12940
14. Bokhari AM, Vinothkumar TS, Albar N, Basheer SN, Felsypremila G, Khayat WF, et al. Barriers in Rubber Dam Isolation Behaviour of Dental Students During Adhesive Restorative Treatments: A Cross-Sectional Study. *Cureus.* 2024;16(4). doi: 10.7759/cureus.58329
15. Frost PM. An audit on the placement and replacement of restorations in a general dental practice. *Primary dental care : journal of the Faculty of General Dental Practitioners (UK).* 2002;9(1):31-6.10.1308/135576102322547548. doi.org/10.1308/135576102322547548
16. Goldstein GR. The longevity of direct and indirect posterior restorations is uncertain and may be affected by a number of dentist-, patient-, and material-related factors. *J Evid Based Dent Pract.* 2010;10(1):30-1. Doi.10.1016/j.jebdp.2009.11.015
17. Kuchibhotla N, Sathyamoorthy H, Balakrishnan S, Somaraju NP, Mohan A, Ginjupalli K, et al. Effect of Bonding Agents on the Shear Bond Strength of Tooth-colored Restorative Materials to Dentin: An In Vitro Study. *J Contemp Dent Pract.* 2024;25(3):245-9.
18. Palotie U, Vehkalahti M. Reasons for replacement and the age of failed restorations in posterior teeth of young Finnish adults. *Acta Odontol Scand.* 2002;60(6):325-9. doi.10.1080/000163502762667333
19. Kimyai S, Mehdipour M, Savadi Oskooe S, Alizadeh Oskooe P, Abbaszadeh A. Reasons for Retreatment of Amalgam and Composite Restorations among the Patients Referring to Tabriz Faculty of Dentistry. *J Dent Res Dent Clin Dent Prospects.* 2007;1(1):27-31. doi.10.5681/joddd.2007.005
20. Mjör IA, Shen C, Eliasson ST, Richter S. Placement and replacement of restorations in general dental practice in Iceland. *Oper. Dent.* 2002;27(2):117-23.
21. Abdal kh, Yari A, Bonyadi M, Shafiei E. Predictive Role of Ectopic Calcifications on Digital Panoramic Radiographs in the West of Iran. *J Res Dent Maxillofac Sci.* 2023 ;8(4).